

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Quest Flooring Pty Ltd
43-55 Mark Anthony Drive
Dandenong South VIC 3175

Test Number : 21-002877
Issue Date : 24/06/2021
Print Date : 24/06/2021

Sample Description Clients Ref : "Astrid"
Tufted twist pile carpet with Action Bac backing
Colour : Grey
Nominal Composition : Solution Dyed Polyester
Nominal Mass per Unit Area/Density : 1700g/m2

AS 4586-2013
Appendix A

Slip Resistance Classification of New Pedestrian Surface Materials Dry Pendulum Test Method

Date of Testing 24/06/2021
Test Temperature 22 °C
Sample Preparation Tested as received without underlay.
Pile Direction Length
Fixed/Unfixed Unfixed
Slider No 96 Batch No 95

Length	1	2	3	4	5	SRV
British Pendulum Number	68	70	70	70	73	70

Classification (Surface tested dry) P5

Equipment: Cooper Pendulum Skid Tester Serial No: 1433-01 Calibrated 08/11/2019
Slider prepared using P400 and 3µm lapping film.

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance and wear on their slip resistance be checked.

240742

52189

Page 1 of 1



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR