

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

## **TEST REPORT**

Client: Quest Flooring Pty Ltd

43-55 Mark Anthony Drive
Dandenong South VIC 3175

Sample Description Clients Ref : "Eureka"

Multi level loop pile carpet Nom Mass: 1088g/m2 Nom thickness: Pile: 10mm Enduse: Flooring

Test Number:

**Issue Date** 

**Print Date** 

24-003356

16/09/2024

16/09/2024

Nominal Composition: Solution Dyed Nyon

Test Method Carpet Institute of Australian Environmental Certification Scheme incorporating ISO

10580: "Resilient, Textile and Laminate Floor Coverings: Evaluation of Volatile Organic

**Compound Emissions"** 

Carpet Institute of Australia Environmental Certification Scheme Spec.	Emission Factor Criterion (24 Hour) µg/m².h	Emission Factor Test Result (24 Hour) µg/m².h
Formaldehyde	<10	<1.3
Acetaldehyde	<20	<1.3
Vinyl Acetate	<400	<1.0
Benzene	<55	<0.5
Toluene	<280	2.7
4-Vinyl cyclohexene	<85	<0.3
Xylenes	<50	<0.3
Styrene	<410	<0.3
1-Methyl-2-Pryrrolidone	<300	<50.0
2-Ethyl-1-hexanol	<50	<2.0
Octanal	<24	<1.0
Nonanal	<24	<1.0
2-ethylhexanoic	<46	<25.0
Napthalene	<20	<0.50
Caprolactam	<120	108.3
4-Phenylcyclohexene	<50	15.3
Hydrocarbons (C10-C14)	<300	192.7
Total Volatile Organic Compound	<500	205.3

Test specimen size

500x400(2 pieces) mm

331143 72648 Page 1 of 2

Australian Wool testing Authority Ltd Copyright - All Rights Reserved Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. The above test results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY.

This document shall not be reproduced except in full and shall be rendered void ifamended or altered.

This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.





MICHAEL A. JACKSON B.Sc.(Hons)



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

## **TEST REPORT**

Client: Quest Flooring Pty Ltd Test Number: 24-003356

43-55 Mark Anthony Drive **Issue Date** 16/09/2024 Dandenong South VIC 3175 **Print Date** 16/09/2024

> Test time 24 Hrs

> Test temperature °C 23 Test humidity 50

Loading factor 0.40 m<sup>2</sup>/m<sup>3</sup>

Air exchange 1 /h

Sealed with aluminium foil, and the back side of test specimen was placed on an inert glass plate to determine the emission of upper surface

Tested by AWTA-JSIC JinAo Testing Co Limited -

China

Test Report Number JA244419

Date of Testing 14/09/2024

## Remarks:

- Formaldeyhde and acetaldehyde were detected using HPLC method with ultraviolet detector, whereas other VOC's substances were detected by Gas chromatography/Mass spectrometry method.
- 2. In this Gas chromatography/Mass spectrometry method, the scan mode of SIM was employed for caprolactum detection, and TIC for others.

Page 2 of 2 331143 72648

Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. The above test results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY.

This document shall not be reproduced except in full and shall be rendered void ifamended or altered.

This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of



L A. JACKSON B.Sc.(Hons)

APPROVED SIGNATORY