

m/s Quest Carpet Manufactures Pty Ltd

43-45 Mark Anthony Drive Dandenong South Vic 3175

Attn: Ms Bridget Sunderland

TEST REPORT No. 137742

LABORATORY REF: P137742

CUSTOMER REFERENCE

VENETIAN

Sample description as provided by customer Mass/unit area 60 oz/yd² 2040 g/m² Construction Details Tufted Secondary Backing Jute Style Cut Pile Twist Order No. BS
Pile Fibre Content 100% SOLUTION DYED NYLON

Colour GREY

Pile Height 12-13 mm

TEST METHOD AS/ISO 9239.1 2003 Reaction To Fire Tests For Floorings Part 1 Determination of the Burning Behaviour Using a Radiant Heat Source. As required by specification C1.10 of the Building Code of Australia.

The test values relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product. Clause 9 of AS/ISO 9239 Part 1.

Conditioning as specified in BS EN 13238,2001

Sample submitted Date Nov 2013

Test Date 26 Nov 2013

ASSEMBLY SYSTEM: OVER UNDERLAY DUNLOP GOVERMENT RED.

The UNDERLAY used was DUNLOPGOVERMENT RED.

Substrate: Non-Combustible

Substrate - 6mm Fibre Reinforced Cement Board to simulate a Non-Combustible Flooring.

The Holding Torque on Specimen Frame was 2Nm.

Initial Test Specimen 1 Length Direction

Specimen 1 Width Direction

Critical Radiant Flux 3.6 kW/m² Critical Radiant Flux 3.5 kW/m²

Full tests carried out in the

Width Direction

AND THE PROPERTY OF THE PARTY O			Philipping Parties and Committee and Committ		
SPECIMEN	Width #1	Width #2	Width #3	Mean	
Critical Radiant Flux (kW/m²)	3.5	3.3	3.5	3.4	
Smoke Development Rate (%.min)	259	283	279	274	

The values quoted below are as required by Specification C1.10 Fire Hazard Properties (Floors) of the Building Code of Australia. The Critical Radiant Flux quoted is the value at Flame-Out/Extinguishment (BCA General Provisions A1.1).

MEAN CRITICAL RADIANT FLUX 3.4 kW/m² MEAN SMOKE DEVELOPMENT PLATE 274 percent-minutes

OBSERVATIONS The samples shrunk away from the heat source and burnt a relatively short distance



M. B. Webb Technical Manager

DATE: 26 Nov 2013

Performance & Approvals Testing No. 15393

Accredited for compliance with ISO/IEC 17025.

PAGE 1 of 2

Clause 9 of AS/ISO 9239 Part 1

The values on Page 2 have no relevance to the Code.

1004 04 09